



## PRODUCT SPECIFICATIONS DOMO Hockey Xtreme

Applications	Hockey
Fibre	Polyethylene / UV-stabilized / Curled / Fibrillated 9.600 dtex 12,7 mm ca. 83 micron
Production Method	Linear tufting
Gauge	5/16"
# stitches / lm	ca. 270 / lm
# tufts / m <sup>2</sup>	ca. 34.020 / m <sup>2</sup>
# piles / m <sup>2</sup>	ca. 68.040 / m <sup>2</sup>
Pile Height	ca. 20 mm
Pile Weight	ca. 1.500 gr / m <sup>2</sup>
Total Height	ca. 22 mm
Total Weight	ca. 2.664 gr / m <sup>2</sup>
Tuft Cloth	Polypropylene, UV-stabilized, ca. 164 gr / m <sup>2</sup>
Backing	Latex, ca. 1.000 gr / m <sup>2</sup>
Infill	Sand (ca. 16 kg, depending on subbase installed)
Roll Width	400 cm
Roll Length	As per lay-out
Colour	Green / Red
Colour Lines	White / Yellow
Colour Fastness	Scale 7 (DIN 54004)
UV-Stability	> 6.000 hours (DIN 53387)
Water Permeability	> 6.10 <sup>-4</sup> m / sec
Inflammability	Class 1 (DIN 51960)
Pile Anchorage	> 30 N
Test Reports	FIH Approval Standard ISA / KNHB 25030081 (Dutch) Labosport / FIH R04-0950 (English)

DOMO Zele NV reserves the right to amend technical specifications on the above mentioned product. Delivered products can slightly differ from these technical data. DOMO Zele NV guarantees the technical quality of the proposed article.